



## CS514L

Special Brass Alloy

Standardization:

**Free-Cutting / Leaded Brass Alloy**

### ALLOY DESCRIPTION

A highly optimized leaded brass designed specifically for high-speed machining, valve, and armature manufacturing. A true industrial standard for mass production.

### CHEMICAL COMPOSITION (% WEIGHT)

Fe (%)	Ni (%)	Al (%)	Cu (%)	Pb (%)	Sn (%)
max 0.05	max 0.3	max 0.02	min 69	max 0.05	max 0.1

### MECHANICAL PROPERTIES (MIN.)

Unspecified

### PHYSICAL PROPERTIES

- Density	8.45 [kg/dm <sup>3</sup> ]
Melting Temperature	~880 - 900 [°C]
Elk. Conductivity	~13 - 15 [MS/m]
Elasticity Modulus	98 [kN/mm <sup>2</sup> ]

### CASTING / MANUFACTURING METHODS

EK	Extrusion (Rod/Profile)
GS	sand casting
GM	Permanent mold casting
GZ	Centrifugal casting

### AREAS OF APPLICATION

Free-Cutting Parts	Valves and Fittings
Fasteners and Screws	Plumbing Connections
Precision Watch Parts	

### MACHINABILITY & CHARACTERISTICS

The addition of lead ensures short and brittle chip breakage during turning and milling, along with low tool wear. Machinability index is the reference standard for extrusion and hot forging parts.

The technical information specified in this document reflects the standard reference values of international EN and DIN norms. Deviations may be observed depending on final production conditions.

**CORUM BRONZE**

E-mail : [info@corumbronz.com](mailto:info@corumbronz.com) | Web : [www.corumbronz.com](http://www.corumbronz.com)