



CuSn4Te1P

Tin Bronze Alloy

Standardization:

Tin Bronze / Phosphor Bronze

ALLOY DESCRIPTION

A hard-surfaced Tin Bronze alloy with high tin content, showing superior resistance to deformation under heavy loads.

CHEMICAL COMPOSITION (% WEIGHT)

Fe (%)	Ni (%)	P (%)	Zn (%)	Sn (%)	Te (%)
max 0.1	max 0.2	0.1 - 0.4	max 0.3	4 - 5	0.5 - 1

MECHANICAL PROPERTIES (MIN.)

Elongation (A)

10

Hardness (HB)

140

PHYSICAL PROPERTIES

Density

8.80 [kg/dm³]

Melting Temperature

~830 - 990 [°C]

Elk. Conductivity

~6 - 8 [MS/m]

Elasticity Modulus

100 [kN/mm²]

CASTING / MANUFACTURING METHODS

EK	Extrusion (Rod/Profile)
GS	sand casting
GM	Permanent mold casting
GZ	Centrifugal casting

AREAS OF APPLICATION

Worm Gears

Heavy Load Bushes

Nuts and Screws

Piston Skirts

Wear Shoes

MACHINABILITY & CHARACTERISTICS

Perfectly withstands high surface pressures. A classic choice for heavy-working worm gears and bearing applications where the load/speed combination is demanding. Corrosion resistance and machinability are well-balanced.

The technical information specified in this document reflects the standard reference values of international EN and DIN norms. Deviations may be observed depending on final production conditions.

CORUM BRONZE

E-mail : info@corumbronz.com | Web : www.corumbronz.com