



CW115C

Pure Copper / Conductive Copper

Standardization:
Pure Copper

ALLOY DESCRIPTION

It is a low-alloy / high-purity copper material accepted as a reference for applications requiring high electrical and thermal conductivity. It is perfectly suited for extreme cold forming and bending operations.

CHEMICAL COMPOSITION (% WEIGHT)

Fe (%)	Si (%)	Mn (%)	P (%)	Al (%)	Pb (%)	Zn (%)
max 0.8	0.8 - 2	max 0.7	max 0.02	max 0.02	max 0.05	max 1.5

MECHANICAL PROPERTIES (MIN.)

Unspecified

PHYSICAL PROPERTIES

- Density	8.90 [kg/dm³]
Melting Temperature	~1080 - 1083 [°C]
Elk. Conductivity	~45 - 58 [MS/m]
Elasticity Modulus	115 [kN/mm²]

CASTING / MANUFACTURING METHODS

EK	Extrusion (Rod/Profile)
GS	sand casting
GM	Permanent mold casting
GZ	Centrifugal casting

AREAS OF APPLICATION

Electrical Conductors	Heat Exchangers
Connectors	Transformer Parts
Switch Components	

MACHINABILITY & CHARACTERISTICS

Due to its pure structure, it is extremely ductile. In machining, it forms long and sticky chips, requiring sharp-geometry tools. Very suitable for soldering and welding. It has good natural resistance to corrosive atmospheres.

The technical information specified in this document reflects the standard reference values of international EN and DIN norms. Deviations may be observed depending on final production conditions.

CORUM BRONZE

E-mail : info@corumbronz.com | Web : www.corumbronz.com